



PREMIUM QUALITY  
WITH REDUCED  
CARBON FOOTPRINT

# HOT-DIP GALVANIZED STEEL STRIP

---

Range of supply  
October 2023

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Mild steels</b>									
<b>EN 10346 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_{90}$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
DX51D	EN 10346	Trans.	-	270 - 500	22	-	-	-	-
DX52D	EN 10346	Trans.	140 - 300	270 - 420	26	-	-	-	-
DX53D	EN 10346	Trans.	140 - 260	270 - 380	30	-	-	-	✓
DX54D	EN 10346	Trans.	120 - 220	260 - 350	36	1.6	0.18	-	✓
DX56D	EN 10346	Trans.	120 - 180	260 - 350	39	1.9	0.21	-	✓
DX57D	EN 10346	Trans.	120 - 170	260 - 350	41	2.1	0.22	-	✓
DX58D	voestalpine	Trans.	110 - 170	250 - 330	43	2.3	0.23	-	✓
<b>VDA 239-100 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_{90}$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
CR1	VDA 239-100	Trans.	140 - 300	270 - 410	28	-	-	-	-
CR2	VDA 239-100	Trans.	140 - 240	270 - 370	34	1.3	0.16	-	✓
CR3	VDA 239-100	Trans.	140 - 210	270 - 350	38	1.8	0.18	-	✓
CR4	VDA 239-100	Trans.	140 - 180	270 - 330	39	1.9	0.20	-	✓
CR5	VDA 239-100	Trans.	110 - 170	260 - 330	41	2.1	0.22	-	✓
CR6	voestalpine	Trans.	110 - 170	250 - 330	43	2.3	0.23	-	✓
<b>Structural steels</b>									
<b>EN 10346</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
S220GD	EN 10346	Long.	≥ 220	≥ 300	20	-	-	-	-
S250GD	EN 10346	Long.	≥ 250	≥ 330	19	-	-	-	-
S280GD	EN 10346	Long.	≥ 280	≥ 360	18	-	-	-	-
S320GD	EN 10346	Long.	≥ 320	≥ 390	17	-	-	-	-
S350GD	EN 10346	Long.	≥ 350	≥ 420	16	-	-	-	-
S390GD	EN 10346	Long.	≥ 390	≥ 460	16	-	-	-	-
S420GD	EN 10346	Long.	≥ 420	≥ 480	15	-	-	-	-
S450GD	EN 10346	Long.	≥ 450	≥ 510	14	-	-	-	-

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Micro-alloyed steels</b>									
<b>EN 10346</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_{90}</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
HX260LAD	EN 10346	Trans.	260 - 330	350 - 430	26	-	-	-	-
HX300LAD	EN 10346	Trans.	300 - 380	380 - 480	23	-	-	-	-
HX340LAD	EN 10346	Trans.	340 - 420	410 - 510	21	-	-	-	-
HX380LAD	EN 10346	Trans.	380 - 480	440 - 560	19	-	-	-	-
HX420LAD	EN 10346	Trans.	420 - 520	470 - 590	17	-	-	-	-
HX460LAD	EN 10346	Trans.	460 - 560	500 - 640	15	-	-	-	-
HX500LAD	EN 10346	Trans.	500 - 620	530 - 690	13	-	-	-	-
<b>VDA 239-100</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_0</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
CR210LA	VDA 239-100	Long.	210 - 300	310 - 410	29	1.0	0.15	-	-
CR240LA	VDA 239-100	Long.	240 - 320	320 - 430	27	-	0.15	-	-
CR270LA	VDA 239-100	Long.	270 - 350	350 - 460	25	-	0.14	-	-
CR300LA	VDA 239-100	Long.	300 - 380	380 - 490	23	-	0.14	-	-
CR340LA	VDA 239-100	Long.	340 - 430	410 - 530	21	-	0.12	-	-
CR380LA	VDA 239-100	Long.	380 - 470	450 - 570	19	-	0.12	-	-
CR420LA	VDA 239-100	Long.	420 - 520	480 - 600	17	-	0.11	-	-
CR460LA	VDA 239-100	Long.	460 - 580	520 - 680	15	-	0.10	-	-

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Bake-hardening steels</b>									
<b>EN 10346</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_{90}</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
HX180BD	EN 10346	Trans.	180 - 240	290 - 360	34	1.5	0.16	30	✓
HX220BD	EN 10346	Trans.	220 - 280	320 - 400	32	1.2	0.15	30	✓
HX260BD	EN 10346	Trans.	260 - 320	360 - 440	28	-	-	30	✓
HX300BD	EN 10346	Trans.	300 - 360	400 - 480	26	-	-	30	✓
<b>VDA 239-100</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_0</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
CR180BH	VDA 239-100	Long.	180 - 240	290 - 370	34	1.1	0.17	30	✓
CR210BH	VDA 239-100	Long.	210 - 270	320 - 400	32	1.1	0.16	30	✓
CR240BH	VDA 239-100	Long.	240 - 300	340 - 440	29	1.0	0.15	30	✓
CR270BH	VDA 239-100	Long.	270 - 330	360 - 460	27	-	0.13	30	✓
<b>High-strength IF steels</b>									
<b>EN 10346</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_{90}</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
HX180YD	EN 10346	Trans.	180 - 240	330 - 390	34	1.7	0.18	-	✓
HX220YD	EN 10346	Trans.	220 - 280	340 - 420	32	1.5	0.17	-	✓
HX260YD	EN 10346	Trans.	260 - 320	380 - 440	30	1.4	0.16	-	✓
<b>VDA 239-100</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_0</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
CR180IF	VDA 239-100	Long.	180 - 240	320 - 400	35	1.2	0.19	-	✓
CR210IF	VDA 239-100	Long.	210 - 270	340 - 420	33	1.1	0.18	-	✓
CR240IF	VDA 239-100	Long.	240 - 300	360 - 440	31	1.0	0.17	-	✓
<b>Carbon-manganese steels</b>									
<b>Special voestalpine grade</b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b><math>A_{80}</math></b>	<b><math>r_{90}</math></b>	<b><math>n_{10-20/Ag}</math></b>	<b>BH<sub>2</sub></b>	<b>E</b>
HT440CMD	voestalpine	Trans.	280 - 380	≥ 440	25	-	-	-	-
HT590CMD	voestalpine	Trans.	420 - 570	≥ 590	14	-	-	-	-

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Dual-phase steels</b>									
<b>EN 10346</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-UE}$	BH <sub>2</sub>	E
HCT450X	EN 10346	Long.	260 - 340	≥ 450	27	-	0.16	30	✓
HCT490X	EN 10346	Long.	290 - 380	≥ 490	24	-	0.15	30	✓
HCT590X	EN 10346	Long.	330 - 430	≥ 590	20	-	0.14	30	✓
HCT780X	EN 10346	Long.	440 - 550	≥ 780	14	-	-	30	-
HCT980X	EN 10346	Long.	590 - 740	≥ 980	10	-	-	30	-
<b>VDA 239-100 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
CR260Y450T-DP	voestalpine	Long.	260 - 340	450 - 560	27	-	0.16	30	✓
CR290Y490T-DP	VDA 239-100	Long.	290 - 380	490 - 600	24	-	0.15	30	✓
CR330Y590T-DP	VDA 239-100	Long.	330 - 430	590 - 700	20	-	0.14	30	✓
CR360Y590T-DP	voestalpine	Long.	360 - 460	590 - 700	19	-	0.14	30	✓
CR440Y780T-DP	VDA 239-100	Long.	440 - 550	780 - 900	14	-	0.11	30	-
CR500Y780T-DP	voestalpine	Long.	500 - 620	780 - 900	13	-	-	30	-
CR550Y980T-DP	voestalpine	Long.	550 - 730	980 - 1130	10	-	-	30	-
CR590Y980T-DP	VDA 239-100	Long.	590 - 740	980 - 1130	10	-	-	30	-
CR660Y980T-DP	voestalpine	Trans.	660 - 810	980 - 1130	10	-	-	30	-
CR700Y980T-DP	VDA 239-100	Long.	700 - 850	980 - 1130	8	-	-	30	-
<b>Dual-phase high-ductility steels (cold rolled dual-phase steels with improved formability)</b>									
<b>VDA 239-100 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
CR330Y590T-DH	voestalpine	Long.	330 - 430	590 - 700	26	-	0.16	30	-
CR440Y780T-DH	VDA 239-100	Long.	440 - 550	780 - 900	18	-	0.13	30	-
CR700Y980T-DH	VDA 239-100	Long.	700 - 850	980 - 1180	13	-	-	30	-

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Complex-phase steels</b>									
<b>EN 10346</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-UE}$	BH <sub>2</sub>	E
HCT780C	EN 10346	Long.	570 - 720	≥ 780	10	-	-	30	-
HCT980C	EN 10346	Long.	780 - 950	≥ 980	6	-	-	30	-
<b>VDA 239-100 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
CR570Y780T-CP	VDA 239-100	Long.	570 - 720	780 - 920	10	-	-	30	-
CR660Y780T-CP	voestalpine	Long.	660 - 820	780 - 960	10	-	-	30	-
CR780Y980T-CP	VDA 239-100	Long.	780 - 950	980 - 1140	6	-	-	30	-
CR900Y1180T-CP	VDA 239-100	Long.	900 - 1100	1180 - 1350	5	-	-	30	-
<b>Complex-phase steels high-ductility (cold rolled complex-phase steels with improved formability)</b>									
<b>voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
CR780Y980T-CH	voestalpine	Long.	780 - 950	980 - 1140	10	-	-	30	-
CR900Y1180T-CH	voestalpine	Long.	900 - 1150	1180 - 1350	7	-	-	30	-

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]
<b>Press-hardening steels</b>					
<b>Special voestalpine grade <sup>1)</sup></b>			<b><math>R_{p0.2}</math></b>	<b><math>R_m</math></b>	<b>A</b>
pht-ultraform 490	unhardened	Trans.	280 - 450	380 - 540	21
pht-ultraform 490	hardened*	Trans.	400	490	16
pht-ultraform 1500	unhardened	Trans.	350 - 480	470 - 700	18
pht-ultraform 1500	hardened*	Trans.	1050	1500	6
pht-directform 490**	unhardened	Trans.	280 - 500	380 - 560	19
pht-directform 490**	hardened*	Trans.	380	490	18
pht-directform 1500	unhardened	Trans.	350 - 600	600 - 850	12
pht-directform 1500	hardened*	Trans.	1050	1500	6
pht-scalefree 490	unhardened	Trans.	280 - 500	380 - 540	21
pht-scalefree 490	hardened*	Trans.	400	490	16
pht-scalefree 1500	unhardened	Trans.	350 - 480	470 - 700	18
pht-scalefree 1500	hardened*	Trans.	1050	1500	6
pht-scalefree 2000	unhardened	Trans.	400 - 650	550 - 800	12
pht-scalefree 2000	hardened*	Trans.	1200	1900	5

<sup>1)</sup> The voestalpine steel grades meet the specifications of VDA 239-500.

\* Mechanical parameters and coating properties in hardened condition are standard values achieved in professional processing of flat sheets. The indicated values are not guaranteed by voestalpine Stahl GmbH

\*\* Indication of preliminary values

Steel grade	Norms and specifications	Test dir.	Yield strength $R_{p0.2}$ [MPa]	Tensile strength $R_m$ [MPa]	Total elong. $A_{80}$ min. [%]	r value min. [-]	n value min. [-]	BH <sub>2</sub> min. [MPa]	Exposed
<b>Hot-rolled low-alloyed or micro-alloyed steels</b>									
<b>VDA 239-100</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
HR380LA	VDA 239-100	Long.	380 - 480	450 - 570	20	-	-	-	-
HR420LA	VDA 239-100	Long.	420 - 520	480 - 600	18	-	-	-	-
HR460LA	VDA 239-100	Long.	460 - 560	520 - 640	16	-	-	-	-
HR500LA	VDA 239-100	Long.	500 - 620	560 - 700	14	-	-	-	-
HR700LA	VDA 239-100	Long.	700 - 850	750 - 950	10	-	-	-	-
<b>Hot-rolled ferritic-bainitic steels</b>									
<b>EN 10346</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
HDT580F	EN10346	Long.	460 - 620	≥ 580	15	-	-	-	-
<b>VDA 239-100 and voestalpine special grade</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
HR440Y560T-FB	voestalpine	Long.	440 - 600	560 - 680	15	-	-	-	-
HR440Y580T-FB	VDA 239-100	Long.	440 - 600	580 - 700	15	-	-	30	-
<b>Hot-rolled complex-phase steels</b>									
<b>EN 10346</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
HDT750C	EN 10346	Long.	620 - 760	≥ 750	10	-	-	-	-
HDT760C	EN 10346	Long.	660 - 830	≥ 760	10	-	-	-	-
<b>VDA 239-100</b>			$R_{p0.2}$	$R_m$	$A_{80}$	$r_0$	$n_{10-20/Ag}$	BH <sub>2</sub>	E
HR660Y760T-CP	VDA 239-100	Long.	660 - 820	760 - 960	10	-	-	30	-



# SURFACES AND FUNCTIONAL SURFACE TREATMENT

Surfaces according to EN 10346 and VDA 239-100					
Product variant	Norms and specifications	Coatings*	Normal surface	Improved surface	Best surface
Zinc coating	EN 10346 VDA 239-100	Z100 - Z450 GI40 - GI115	NA, MA -	MB U	MC** E**
Zinc-iron coating	EN 10346 VDA 239-100	ZF100 - ZF120 GA40 - GA50	RA -	RB U	RC E
corrender Zinc-magnesium coating	EN 10346 VDA 239-100	ZM70 - ZM310 ZM30 - ZM50	NA, MA -	MB U	MC** E**

\* Other coatings upon request.

\*\*The zinc and zinc-magnesium coating variants are available in MC/E surface quality with reduced waviness, texplus®.

Functional surface treatment				
Product variant	clearcover® Cr-free passivation (and oiled)	multiface® sealant	Forming aid and oiled	Oiled (e.g. prelube2)
Zinc coating	√ (√)	√	√	√
Zinc-iron coating	√ (√)	-	√	√
corrender Zinc-magnesium coating	√ (√)	√	-	√



Premium quality with reduced carbon footprint

Hot-dip galvanized steel strip – greentec steel Edition

Max. carbon footprint 2.13 kg CO<sub>2</sub>e per kg of steel <sup>1)</sup>

<sup>1)</sup> per EN 15804+A2 (EPD methodology) cradle to gate

All products, dimensions and steel grades listed in each voestalpine supply range are available as greentec steel Edition.

# DIMENSIONS

Available dimensions: wide strip (coil)				
Product variant	Thickness [mm]	Width max. [mm]	Outside diameter max. [mm]	Inside diameter [mm]
Zinc coating	0.45 - 4.00	1730	2000	500 / 600
Zinc-iron coating	0.45 - 2.30	1730	2000	500 / 600
corrender Zinc-magnesium coating	0.45 - 2.30	1730	2000	500 / 600

Available dimensions: slit (slit strip)				
Product variant	Thickness [mm]	Strip width min. [mm]	Outside diameter [mm]	Inside diameter [mm]
Zinc coating	0.45 - 4.00	10	700 - 2000	500 / 600
Zinc-iron coating	0.45 - 2.30	10	700 - 2000	500 / 600
corrender Zinc-magnesium coating	0.45 - 2.30	10	700 - 2000	500 / 600

Available dimensions: cut-to-length (sheet)				
Product variant	Thickness [mm]	Width min. [mm]	Length [mm]	Package weight max. [t]
Zinc coating	0.45 - 4.00	210	200 - 6700	6
Zinc-iron coating	0.45 - 2.30	210	200 - 6700	6
corrender Zinc-magnesium coating	0.45 - 2.30	210	200 - 6700	6

Indicated references are standard values. The available combinations of widths and thicknesses and supply forms vary depending on the steel grade and coating system. Limitations are possible depending on thickness.

This document provides an overview of the hot-dip galvanized steel strip products supplied by the voestalpine Steel Division. Other grades are available upon request. Please find further information and downloads under the following link:

[www.voestalpine.com/steel](http://www.voestalpine.com/steel)

[www.voestalpine.com/surface-treatments/Produkte](http://www.voestalpine.com/surface-treatments/Produkte)

The information and product properties contained in this printed material are non-binding and serve the sole purpose of technical orientation. They do not replace individual advisory services provided by our sales and customer service teams. The product information and characteristics set forth herein shall not be considered as guaranteed properties unless explicitly stipulated in a separate contractual agreement. For this reason, voestalpine shall not grant any warranty nor be held liable for properties and/or specifications other than those subject to explicit agreement. This also applies to the suitability and applicability of products for certain applications as well as to the further processing of materials into final products. All application risks and suitability risks shall be borne by the customer. The General Terms of Sale for Goods and Services of the voestalpine Steel Division shall apply to all materials supplied by the voestalpine Steel Division and can be accessed using the following link: [www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale](http://www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale)

Technical changes are reserved. Errors and misprints are excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.

10/2023

**voestalpine Steel Division**  
voestalpine-Straße 3  
4020 Linz, Austria  
productmanagement@voestalpine.com  
[www.voestalpine.com/steel](http://www.voestalpine.com/steel)

**voestalpine**  
ONE STEP AHEAD.